

HYD03A

FOR POLYMERS AND MORE

DESCRIPTION

HYD03A is manufactured for water and moisture control applications by selectively removing water from the surrounding environment. The addition of 3A to polymer mixtures will create an adsorbent matrix that prevents the formation of bubbles and increases the lifespan of adhesives, paints, polymers, sealants, and more. This molecular sieve offers a high adsorption capacity in both static and dynamic adsorption processes.

- used to increase the integrity of polymer mixtures
- capable of removing water and preventing the formation of gas and bubbles
- allows polymer mixtures to offer a longer lifespan
- offers low dust and attrition properties as well as low gas desorption

CHEMICAL FORMULA



SPECIFICATIONS

Molecular Sieve		Beads						
HYD03A		20x35 Mesh	18x35 Mesh	16x25 Mesh	12x18 Mesh	10x16 Mesh	10x14 Mesh	7x12 Mesh
Property	Unit							
Diameter	mm	0.5-0.8	0.5-1.0	0.8-1.2	1.0-1.5	1.2-1.8	1.5-2.0	1.6-2.5
Bulk Density	g/mL (lb/ft ³)	≥0.75 (≥46.8)	≥0.75 (≥46.8)	≥0.75 (≥46.8)	≥0.75 (≥46.8)	≥0.75 (≥46.8)	≥0.74 (≥46.2)	≥0.74 (≥46.2)
Static Water Adsorption	wt%	≥20.0	≥20.0	≥20.0	≥20.0	≥20.0	≥20.0	≥20.0
Moisture Content	wt%	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0
Packaging Options	Super Sack options; 150kg (330.7lb) / Drum; 25kg (55.1lb) / carton with foil bag							

INDUSTRIES USED

coatings
plastic
sealants

glue
polymer mixtures

paint
refrigerants

STORAGE AND HANDLING

As an adsorbent, molecular sieve should not be left exposed to open air and should be stored in dry conditions with air-proof packaging. This product should not be exposed to temperatures exceeding 230°C (450°F).

CONNECT WITH US...

Hengye Inc.

11999 Katy Frwy, Suite 588

Houston, Texas 77079

Office (832) 288-4288

Fax (832) 288-4230

info@hengyeinc.com



HENGYE



ISO 9001:2008



ISO 14001:2004